

Gairome Clay A (A 級蛙目土)

Item	Result (%)	
SiO₂	46.9	
Al₂O₃	36.8	
Fe₂O₃	1.29	
CaO	0.17	
MgO	0.21	
K₂O	0.41	
Na₂O	0.07	
TiO₂	0.60	
Ig. Loss @1050°C	13.5	
Moisture	Noodle	Dry
	≤25%	≤10%
Drying Shrinkage	Around 1~2% (water content 30%, 105 °C)	
Firing Shrinkage	Around 1~2% (1220 °C)	
Total Shrinkage	Around 13~16%	
Bulk Density	2.6g/cm ³	

*Above specification are based on internal testing.

Country of Origin: Japan